United Adhesives, Inc.



Asia +86 (139) 5605 4600 North America & Europe +1 (224) 436 0077 Sales@UnitedAdhesives.com

www.UnitedAdhesives.com

UF 1220

Very Low Coefficient of Thermal Expansion Epoxy Underfill

Typical Properties			
Property	Unit	Value	Test Method
Color of Component		Blue	Visual
Density	Gram /cc	1.72	ASTM D792
Viscosity at 25°C	cps	12,000	ASTM D2196
Property as Cured			
Color		Blue	Visual
Young's modulus	GPa	8.8	DMA
Dielectric Constant	@1000Hz	3.5	ASTM D150
Dielectric Strength	Volt/mil AC	> 500	ASTM D149
Volume Resistivity	Ohm-cm	> 10E+14	ASTM D257
Coefficient of Thermal Expansion	ppm/C	48 (@ > Tg) 10 (@ < Tg)	IPC-TM-650
Adhesion (Al/Al lap shear)	Psi	> 1800	ASTM D1002
Тд	°C	145	DMA
Temperature Usage	°C	-80 to 200	TGA
Cure Profile			
Cure at 115°C	min	50	Durometer
Cure at 125°C	min	25	Durometer
Cure at 150°C	min	15	Durometer
Pot / Work Life at 25°C (after warmed up)	hr	24	Viscosity double

These figures are only intended as a guide and should not be used in preparing specifications.

The adhesive is a pre-mixed adhesive as one part for easier

adhesive to about 50°C, to promote faster capillary flow.

applying. In order to keep longer usage life, please always store the

original or left material in freezer (- 40°C). For some applications, it

is recommended to warm the applied surface to ~ 105C, and/or the

We recommend running preliminary tests to optimize conditions for

the particular application. Comprehensive processing instructions

can be obtained by contacting directly to United Adhesives, Inc.

Characteristics

UF 1220 is an epoxy-based, very low coefficient of thermal expansion (CTE) adhesive. It is used as underfill or encapsulant for chip-on-board, bare die, BGA, flip-chip, CSP, and other electronic applications. It is a one-part, capillary flow formulation that cures at elevated temperature to provide strong bonding to silicon, flip chip, BGA, ceramics, FR4, LTCC, aluminum, copper, stainless steel, etc. with minimized thermal mismatching stress. Its extremely low CTE provides better thermal cycle performances. UF 1220 is dispensable. For underfilling, it is recommended to warm the applied surface to ~ 105°C to promote faster capillary flow.

Special Features and Benefits

- Very low CTE for stress compliance
- · Fast flow and capillary flow
- High thermal stability
- High structural bonding strength
- Low bleeding, low volatile
- Low ionic content

Typical Applications

- Aerospace electronics
- Automotive electronics
- Semiconductor and Telecommunications
- Bonding of die to LTCC, AI, Cu
- Underfilling of BGA, Bare die, flip-chip, CSP
- · Chip-on-board bonding / encapsulating

UF 1220 has a shelf life of at least 3 months when stored in freezer (-40°C) in the originally sealed container.

UF 1220 has a shelf life of at least 3 months when stored in freezer $(-40^{\circ}C)$ in the originally sealed container. The 'Best use before end' date of each batch appears on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety information

General hygiene regulations should be observed. Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from United Adhesives, Inc.

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infingement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose. For technical, quality, or product safety questions, please contact directly to United Adhesives Inc.

Processing Instruction