

UF 1225

Moisture Resistance Epoxy Underfill

Typical Properties			
Property	Unit	Value	Test Method
Color of Component		Blue	Visual
Density	Gram /cc	1.42	ASTM D792
Viscosity at 25°C	cps	9,000	ASTM D2196
Property as Cured			
Color		Blue	Visual
Young's modulus	GPa	3.7	DMA
Dielectric Constant	@1000Hz	3.5	ASTM D150
Dielectric Strength	Volt/mil AC	> 500	ASTM D149
Volume Resistivity	Ohm-cm	> 10E+14	ASTM D257
Coefficient of Thermal Expansion	ppm/C	53 (@ < Tg) 125 (@ > Tg)	IPC-TM-650
Adhesion (Al/Al lap shear)	Psi	> 2200	ASTM D1002
Tg	°C	150	DMA
Moisture Absorption (85°C 85%RH 1000 hours)	% Wt	< 0.2%	TGA
Temperature Usage	°C	-80 to 200	TGA
Cure Profile			
Cure at 125°C	min	30	Durometer
Cure at 150°C	min	20	Durometer
Pot / Work Life at 25°C (after warmed up)	hr	24	Viscosity double

These figures are only intended as a guide and should not be used in preparing specifications.

Processing Instruction

The adhesive is a pre-mixed adhesive as one part for easier applying. In order to keep longer usage life, please always store the original or left material in freezer (-40°C). For some applications, it is recommended to warm the applied surface to ~105°C, and/or the adhesive to about 50°C, to promote faster capillary flow.

We recommend running preliminary tests to optimize conditions for the particular application. Comprehensive processing instructions can be obtained by contacting directly to United Adhesives, Inc.

Characteristics

UF 1225 is a silicone-toughened epoxy adhesive for under filling or encapsulating chip-on-board, bare die, BGA, flip-chip, CSP, and other electronic applications. It is a one-part, capillary flow formulation that cures at elevated temperature to provide strong bonding to silicon, flip chip, BGA, ceramics, FR4, LTCC, aluminum, copper, stainless steel, etc. The silicone rubber toughening improves the fracture toughness of the underfill and moisture resistance, which provides better thermal cycle performances and humidity cycles. UF1225 is dispensable. For underfilling, it is recommended to warm the applied surface to ~105°C to promote faster capillary flow.

Special Features and Benefits

- Low moisture absorption
- High fracture toughness
- High structural bonding strength
- Fast flow and capillary flow
- High thermal stability
- Low bleeding, low volatile
- Low ionic content

Typical Applications

- Aerospace electronics
- Automotive electronics
- Semiconductor and Telecommunications
- Bonding of die to LTCC, Al, Cu
- Underfilling of BGA, Bare die, flip-chip, CSP
- Chip-on-board bonding / encapsulating

UF 1225 has a shelf life of at least 6 months when stored in freezer (-40°C) in the originally sealed container. The 'Best use before end' date of each batch appears on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety information

General hygiene regulations should be observed. Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from United Adhesives, Inc.

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose. For technical, quality, or product safety questions, please contact directly to United Adhesives Inc.